

THOMSON
★
DELPHION

RESEARCH

PRODUCTS

INSIDE DELPHION

My Account

Search: Quick/Number Boolean Advanced Derwent

Help

The Delphion Integrated View

Get Now: ☒ PDF | [More choices...](#)

Tools: Add to Work File: Create new Work File Go

View: [INPADOC](#) | Jump to: Top Go to: [Derwent](#) [Email this to a friend](#)

🔍 Title: **JP04300232A2: COMPOSITE GYPSUM BOARD AND ITS PRODUCTION**

🔍 Derwent Title: Composite gypsum board having improved bending strength and surface precision - is mfd. by mixing alpha-type hemi:hydrate gypsum, dried waste paper pulp, inorganic powder and water, moulding and curing [[Derwent Record](#)]

🔍 Country: JP Japan

🔍 Kind: A

🔍 Inventor: YOSHIDA HIROSHI;
SAKAI MATSUNARI;
WATANABE KOJI;
KUBOTA HACHIRO;

🔍 Assignee: CHUBU ELECTRIC POWER CO INC
ONODA CEMENT CO LTD
[News, Profiles, Stocks and More about this company](#)

🔍 Published /
Filed: 1992-10-23 / 1991-03-29

🔍 Application
Number: JP1991000066229

🔍 IPC Code: [C04B 28/14](#); [C04B 14/02](#); [C04B 16/02](#); [C04B 28/14](#);


🔍 Priority
Number: 1991-03-29 JP1991000066229

🔍 Abstract: **PURPOSE:** To obtain a composite gypsum board having improved flexural strength and surface accuracy by adding water to a mixture of α -gypsum hemihydrate, dried waste paper pulp and inorganic powder, mixing and forming the mixture and curing the formed product.

CONSTITUTION: Raw materials composed of 95-45wt.% of α -gypsum hemihydrate having a Blaine specific surface area of 1,000-8,000cm²/g, 3-45wt.% of dried waste paper pulp having a diameter of 20-100 μ m and a length of 50-3,000 μ m and 2-20-wt.% of inorganic powder (shirasu balloon) having a fineness of 20-500 μ m are mixed with each other by a mixer, added with 20-60wt.% of water (based on 100wt.% of the α -gypsum hemihydrate) using a spray nozzle under pressure and further mixed. The obtained mixture is transferred to a forming machine and formed in the form of a mat. The mat is transferred to a press, pressed under the condition of 5-50kgf/cm² to obtain a board, cured at room temperature to 45°C and dried at 70-90°C to obtain the objective composite gypsum board having a bulk density of 0.8-1.5 and a flexural strength of 50-150 kgf/cm².

COPYRIGHT: (C)1992,JPO&Japio

🔍 Family: None




[View
Image](#)

1 page

Forward
References:

Go to Result Set: Forward references (1)

PDF	Patent	Pub.Date	Inventor	Assignee	Title
	US6572697	2003-06-03	Gleeson; James A.	James Hardie Research Pty Limited	Fiber cement building materials with low density additives

Other Abstract
Info:

CHEMABS 118(14)130760P CAN118(14)130760P DERABS C92-403122 DERC92-403122



[Nominate this for the Gallery...](#)

Copyright © 1997-2004
The Thomson Corporation

[Subscriptions](#) | [Web Seminars](#) | [Privacy](#) | [Terms & Conditions](#) | [Site Map](#) | [Contact Us](#) | [Help](#)